Effective g-factor tensor for carriers in IV-VI semiconductor quantum wells

E. Ridolfi 1, E. A. de Andrada e Silva 2 and G. C. La Rocca 3

¹ Instituto de Física, Universidade Federal Fluminense, 24210-346, Niterói, Rio de Janeiro, Brazil ² Instituto Nacional de Pesquisas Espaciais, C.P. 515,

12201-970 São José dos Campos, São Paulo, Brazil and

³ Scuola Normale Superiore and CNISM, Piazza dei Cavalieri 7, I-56126 Pisa, Italy

A theory for the electron (and hole) g-factor in lead-salt IV-VI semiconductor quantum wells (QWs) is presented. An effective Hamiltonian for the QW electronic states in the presence of an external magnetic field is introduced within the envelope-function approximation, based on the multi-band $k \cdot p$ Dimmock model for the bulk. The mesoscopic spin-orbit (Rashba type) and Zeeman interactions are taken into account on an equal footing and the effective g-factor in symmetric quantum wells (g_{OW}^{*}) is calculated analytically for each non-equivalent conduction (and valence) band valley, and for QWs grown along different crystallographic directions.

INTRODUCTION I.

Since the development of the first semiconductor electronic devices the lead-salt IV-VI semiconductor compounds have attracted great interest both for their applications (as narrow and direct gap materials for infrared lasers and detectors) and for the interesting relativistic physics involved in their electronic properties [1]. For example, the spin-orbit interaction in these compounds is particularly strong and is directly responsible for the opening of the fundamental gap in the bulk [2], as well as for the pure Rashba splitting in asymmetric QWs [3]. IV-VI semiconductor nanostructures have been successfully fabricated and applied to different electronic devices [4–7]. More recently they have been at the center of the research on the physics of the topological insulators and new spintronic devices [8, 9].

However, the electronic structure of the IV-VI nanostructures, specially in the presence of a magnetic-field is not well known. In particular, the quantum confinement effects on the g-factor of the carriers (electrons and holes) are not well understood and form the main focus of the present contribution. Within the multi-band envelope function approximation, we present a simple theory for the electronic states of IV-VI QWs in the presence of a magnetic field, with analytical results for the g-factor tensor, as a function of both growth and magnetic field directions. The approach recently introduced to describe the g-factor of carriers confined in III-V QWs is here extended to the case of multi-valley and anisotropic semiconductor structures.

We recall that the g-factor is a fundamental physical quantity which determines the spin splitting of the electronic states in response to an external magnetic field (Zeeman effect). Due to band structure effects, for electrons (or quasi-particles) in a semiconductor, the corresponding g-factor is renormalized from the bare value 2 and is referred to as the effective g-factor (g^*) , in analogy with the effective mass m^* . In a QW, g^* is further renormalized by the confining potential, can be tuned and is a main parameter for spintronic applications. Here we discuss the physics of such mesoscopic g-factor renormalization in the case of IV-VI *PbTe*-like QWs.

EFFECTIVE HAMILTONIAN II.

We first derive an effective Hamiltonian for the electronic states starting from the Dimmock $k \cdot p$ model for the bulk [2]. Considering the four equivalent valleys at the L-point as independent of each other and using a coordinate system with the z-axis along the main axis of the ellipsoidal valley, the conduction (or valence) band can be described by the following (energy dependent) effective 2x2 Hamiltonian [10, 11]:

$$H_{eff} = \left[\frac{E_g}{2} + P_{\parallel}^2 \hat{k}_z \gamma \hat{k}_z + P_{\perp}^2 \hat{k}_x \gamma \hat{k}_x + P_{\perp}^2 \hat{k}_y \gamma \hat{k}_y\right] + H_{so} ,$$
(1)

with

$$H_{so} = P_{\parallel}P_{\perp}(\gamma \begin{bmatrix} \hat{k}_{y}, \hat{k}_{z} \end{bmatrix} + \begin{bmatrix} \hat{k}_{y}, \gamma \end{bmatrix} \hat{k}_{z} - \begin{bmatrix} \hat{k}_{z}, \gamma \end{bmatrix} \hat{k}_{y})i\sigma_{x}(2)$$
$$+ P_{\parallel}P_{\perp}(\gamma \begin{bmatrix} \hat{k}_{z}, \hat{k}_{x} \end{bmatrix} + \begin{bmatrix} \hat{k}_{z}, \gamma \end{bmatrix} \hat{k}_{x} - \begin{bmatrix} \hat{k}_{x}, \gamma \end{bmatrix} \hat{k}_{z})i\sigma_{y}$$
$$+ P_{\perp}^{2}(\gamma \begin{bmatrix} \hat{k}_{x}, \hat{k}_{y} \end{bmatrix} + \begin{bmatrix} \hat{k}_{x}, \gamma \end{bmatrix} \hat{k}_{y} - \begin{bmatrix} \hat{k}_{y}, \gamma \end{bmatrix} \hat{k}_{x})i\sigma_{z},$$

 $\gamma=1/(E\!+\!\frac{E_g}{2})$ and where the energy origin was set at the middle of the gap (of width E_q), x and y are the transverse directions, $\vec{\sigma}$ the Pauli matrices vector, P_{\parallel} (P_{\perp}) the usual kp momentum matrix element parallel (perpendicular) to the valley main axis, and $(\hat{k}_x, \hat{k}_y, \hat{k}_z)$ the electron wave-vector operator. Note that H_{eff} is the Dimmock four-band model projected into the conduction band and that it is written in a form which facilitates the inclusion of both the magnetic field and the band-gap variation in a QW structure. Note also that in the bulk (and zero field), γ is constant, the envelope function is simply $e^{i\vec{k}\cdot\vec{r}}$, the k-vector components are c-numbers and all commutators above are equal to zero, so that one obtains the well known non-parabolic dispersion relation around the gap of these narrow-gap semiconductors, described by the energy dependent effective masses $m_{\parallel,\perp} = \frac{\hbar^2}{2P_{\parallel,\perp}^2} (E + \frac{E_g}{2}),$

i.e.:

$$E = \frac{E_g}{2} + \frac{\hbar^2}{2} \left(\frac{k_{\parallel}^2}{m_{\parallel}(E)} + \frac{k_{\perp}^2}{m_{\perp}(E)} \right), \qquad (3)$$

where $k_{\perp}^2=k_x^2+k_y^2.$ Besides the energy gap $E_g,$ the only parameters are P_{\parallel} and P_{\perp} which are fixed with the measured band-edge effective mass $m_{\parallel,\perp}^*$, i.e. $P_{\parallel,\perp} = \sqrt{\hbar^2 E_g / 2m^*_{\parallel,\perp}}$, and are assumed constant along the QW structure in the envelope function approximation. A specular equation is similarly obtained for the valence band. Such model has been shown to describe very well the band structure of the lead-salts near the fundamental band gap and is here used to study the QW in a \vec{B} field problem. m In a QW the lack of translation symmetry along the growth direction, in general, breaks the valley degeneracy, and it is convenient to use a new coordinate system where now the z-axis is along the growth direction (which, except for the longitudinal valley in a [111] QW, is not parallel to the valley main axis). So that $E_g = E_g(z)$ and therefore $\gamma = \gamma(z)$ (the center of the band-gap is also allowed to vary along the growth direction due to the band-offset described by a step function Q(z)). In the cases of interest, such new QW coordinate system is obtained from the valleysystem used above with a simple rotation around a transverse direction (x), so that the components of a vector \vec{v} are given by: $v_x = v_{x'}$, $v_y = v_{y'} \cos(\theta) + v_{z'} \sin(\theta)$ and $v_z = v_{z'} \cos(\theta) - v_{y'} \sin(\theta)$, where θ is the angle of rotation and the valley-system is now denoted by (x', y', z').

In order to include the effects of an external magnetic field \vec{B} , one then adds the Zeeman term of the bulk, i.e. $\frac{1}{2}\mu_0(g_{\parallel}B_{z'}\sigma_{z'}+g_{\perp}(B_{x'}\sigma_{x'}+B_{y'}\sigma_{y'}))$, where g_{\parallel} and g_{\perp} are the g-factor Dimmock parameters for the bulk conduction band valleys, which (as for the effective masses) are fixed with the measured band-edge g-factor $g_{\parallel,\perp}^*$ (including then the contributions from the remote bands); and makes also the fundamental substitution $\vec{k} = -i\nabla + (e/\hbar)\vec{A}$, in the k-vector operator.

Following the classic work by Stern and Howard [12], we use the gauge $\vec{A} = (B_y z - B_z y, -B_x z, 0)$, set the envelope function as $\mathcal{F}(\vec{r}) = e^{ik_x x} F(y, z)$ (since H_{eff} does not depend on x), perform the unitary transformation (or use a phase) so that

$$F = e^{-iD(\hat{k}_y z - b_x z^2/2)} f$$

with

$$D = D(\theta) = \frac{\left(P_{\parallel}^2 - P_{\perp}^2\right)\sin(\theta)\cos(\theta)}{P_{\parallel}^2\cos(\theta)^2 + P_{\perp}^2\sin(\theta)^2}.$$

(in order to simplify and eliminate the term linear in \hat{k}_y) and use also the translation operator property

$$e^{iak_y}f(y) = f(y+a)e^{iak_y}f(y)$$

After simple algebra, one obtains the following effective Hamiltonian (as a sum of kinetic, mesoscopic potential, Zeeman and Rashba terms):

$$H_{eff} = H_{ki} + V(z) + H_Z + H_R,$$
 (4)

where $V(z) = E_g(z)/2 + Q(z)$,

$$H_{ki} = \frac{\hbar^2}{2} [\hat{k}_z \frac{1}{m_3} \hat{k}_z + \frac{(\hat{k}_y - b_x z)^2}{m_2} + \frac{(k_x + b_y z - b_z (y + Dz))^2}{m_1}]$$
(5)

(with $\vec{b} = (e/\hbar)\vec{B}$, $m_1 = m_{\perp}$, $m_2 = \cos(\theta)^2 m_{\perp} + \sin(\theta)^2 m_{\parallel}$ and $m_3 = m_{\parallel}m_{\perp}/(m_{\perp}\cos(\theta)^2 + m_{\parallel}\sin(\theta)^2))$, where the energy and z-dependent effective masses are given by

$$m_{\parallel,\perp}(E,z) = \frac{\hbar^2}{2P_{\parallel,\perp}^2} \left(E + \frac{E_g(z)}{2} - Q(z)\right), \qquad (6)$$

the Zeeman term

$$H_Z = \frac{\mu_0}{2} \vec{B} \cdot [\tilde{g}_0 + \frac{4m_e}{\hbar^2} (\gamma_{so} \tilde{g}_{so} + z \frac{\partial \gamma_{so}}{\partial z} \tilde{g}_{qw})] \vec{\sigma} , \quad (7)$$

where the \tilde{g} s are the components of the effective g-factor tensor (given bellow) and

$$\gamma_{so} = \frac{P_{\parallel}P_{\perp}}{E + \frac{E_g(z)}{2} - Q(z)}$$

finally

$$H_R = \left(\frac{\partial \gamma_{so}}{\partial z}\right) \vec{B}_R(k_x, \hat{k}_y) \cdot \vec{\sigma} , \qquad (8)$$

with the effective k-dependent Rashba field given by

$$\vec{B}_R = (-\hat{k}_y, (rs^2 + c^2)k_x, (r-1)sck_x)$$

where, to simplify, we use $c = \cos(\theta)$, $s = \sin(\theta)$ and the anisotropy parameter

$$r = \frac{P_{\perp}}{P_{\parallel}} = \sqrt{\frac{m_{\parallel}^*}{m_{\perp}^*}} \,.$$

III. QW EFFECTIVE G-FACTOR TENSOR

As the main result, one gets the QW effective g-factor tensor (Eq. (7)) given by the following three components:

$$\tilde{g}_{0} = \begin{pmatrix} g_{\perp} & 0 & 0\\ 0 & g_{\perp}c^{2} + g_{\parallel}s^{2} & (g_{\parallel} - g_{\perp})sc\\ 0 & (g_{\parallel} - g_{\perp})sc & g_{\perp}s^{2} + g_{\parallel}c^{2} \end{pmatrix}, \quad (9)$$

$$\tilde{g}_{so} = \begin{pmatrix} 1 & 0 & 0\\ 0 & rs^2 + c^2 & (r-1)sc\\ 0 & (r-1)sc & rc^2 + s^2 \end{pmatrix},$$
(10)

and

$$\tilde{g}_{qw} = \begin{pmatrix} 1 & 0 & 0 \\ 0 & rs^2 + c^2 & (r-1)sc \\ 0 & -(rs^2 + c^2)(\frac{y}{z} + D) & -(r-1)sc(\frac{y}{z} + D) \end{pmatrix}.$$
(11)

For example, the result for the bulk is simply recovered by noting that in this case γ_{so} is constant and, in the valley coordinate system (i.e. with c=1 and s=0), one then has:

$$\tilde{g}_{bulk} = \begin{pmatrix} g_{\perp}^* & 0 & 0\\ 0 & g_{\perp}^* & 0\\ 0 & 0 & g_{\parallel}^* \end{pmatrix},$$
(12)

with

$$g_{\perp}^* = g_{\perp} + \frac{4m_e}{\hbar^2} \gamma_{so} \tag{13}$$

and

$$g_{\parallel}^* = g_{\parallel} + \frac{4m_e}{\hbar^2} \gamma_{so} r \,, \tag{14}$$

which are energy dependent and can also be written as a function of the above defined parallel and perpendicular effective masses, i.e.:

$$g_{\perp}^{*}(E) = g_{\perp} + \frac{2m_{e}}{\sqrt{m_{\perp}(E)m_{\parallel}(E)}}$$

and

$$g_{\parallel}^*(E) = g_{\parallel} + \frac{2m_e}{m_{\perp}(E)} \,.$$

Note that the Dimmock parameters g_{\perp} and g_{\parallel} correspond to the remote bands contribution and that the III-V-like spherical symmetric case is obtained only with $g_t = g_l$ and r = 1.

It is the third term in H_z above, proportional to $\frac{\partial \gamma_{so}}{\partial z}$, that gives the QW contribution due to the mesoscopic quantum confinement. As shown in Ref.[13] for GaAs QWs, the QW effective g-factor (g_{QW}^*) can conveniently be calculated with perturbation theory. Using the ground state of $H_0 = H_{ki}(\vec{B} = 0) + V(z)$, one simply calculates $\langle f_0|H_Z|f_0 \rangle = \bar{H}_z$ where $H_0f_0 = E_0f_0$. Next, following the same scheme, we consider the lead-salt QW effective g-factors for different growth directions and nonequivalent valleys. Such approach for the calculation of g_{QW}^* is for instance much simpler and more transparent then that used before for the L-valley electrons in SiGe QW structures [14].

IV. [111] AND [100] QWS

We now consider common symmetric QWs grown along the [111] and [100] crystallographic directions and



FIG. 1. Schematic illustration of the QW coordinate system, of the L-valleys projected into the QW plane for growth direction (z) along both [111] and [100] crystallographic directions (in A and B respectively) and in C, of the oblique valley (the filled one) orientation.

with interfaces at $z = \pm L/2$. For [111] QWs, the four equivalent L-valleys in the bulk split into one longitudinal and three oblique ones, while for [100] QWs we deal with four degenerate oblique valleys. In the expressions above, all one has to do is to set (s = 0; c = 1) for the longitudinal valley and for the oblique valleys $(s = 2\sqrt{2}/3;$ c = 1/3) for [111] QWs and $(s = \sqrt{2/3}; c = 1/\sqrt{3})$ for [100] QWs. The applied magnetic field is considered both longitudinal (along the growth direction) and transverse (in the QW plane) and the corresponding effective g-factors $g_{QW,l}^2$ and $g_{QW,t}^2$ are calculated.

For the numerical results and illustrative example, PbSnTe/PbTe QWs are considered with the following low-temperature empirical parameters: $E_g^{PbTe} = 0.19$ $eV, m_{\parallel}^{*,PbTe} = 0.24 m_e, m_{\perp}^{*,PbTe} = 0.024 m_e$ [10], $g_{\parallel}^{*(PbTe)} = 58, g_{\perp}^{*(PbTe)} = 15$ [15, 16] and $E_g^{PbSnTe} = 0.1$ eV. The Dimmock parameters g_{\parallel} (= -24.3) and g_{\perp} (= -11.4) are determined by $g_{\parallel}^{*(PbTe)}$ and $g_{\perp}^{*(PbTe)}$ respectively, and assumed constant along the structure. A



FIG. 2. Effective g-factor for the longitudinal valley electrons in PbSnTe/PbTe [111] QWs and longitudinal B-field (along the growth direction) as a function of the well width. The limiting (well and barrier) energy dependent bulk effective g-factors are also plotted, giving the effect of the QW confinement energy shift.

symmetrical 0.5 band-offset is used. The unperturbed ground state energy E_i and corresponding envelope function $f_0 = f_i(z)$ for each non-equivalent valley, i.e with i = l (longitudinal) or i = o (oblique), are calculated exactly following standard procedure as described in references [10, 13].

A. Longitudinal valley

For the longitudinal valley and longitudinal magneticfield $\vec{B} = B\hat{z}$ one gets the QW effective g-factor simply given by the bulk average, in perfect analogy to the III-V case, i.e.

$$g_{QW,l}^* = \langle g_{\parallel}^* \rangle = g_{\parallel,w}^*(E_l) P_w + g_{\parallel,b}^*(E_l) P_b , \qquad (15)$$

where P_j $(= \int_j |f_l(z)|^2 dz)$ is the probability to find the electron in the well (j = w) or in the barrier (j = b) (note that for the longitudinal valley D = 0 so that for the longitudinal field, there is no QW or interface contribution, i.e. from \tilde{g}_{qw}). To simplify the notation, from now on, as above, the energy dependent parameters are meant to be calculated at E_l or at E_o depending on whether it is a longitudinal or an oblique valley effective QW g-factor (similarly, f_0 stands for either f_l or f_o).

In Figure 2, $g_{QW,l}^*$ for electrons (or holes) in PbSnTe/PbTe QWs is plotted as a function of the well width. For comparison and as limiting cases, the energy dependent bulk g-factors for both PbTe and PbSnTe are also plotted. See for instance that as expected $g_{QW,l}^*$ tends to the well (PbSnTe) bulk value and to the barrier bulk value in the limits of L going to infinity and to zero respectively.



FIG. 3. Effective g-factor for the longitudinal valley electrons in PbSnTe/PbTe [111] QWs and transverse magnetic field $g^*_{QW,t}$ as a function of the well width. For the different contributions to QW g-factor renormalization (i.e., barrier penetration, confinement energy shift and interface SO contributions), the energy dependent barrier and well g-factors, as well as the average bulk g-factor, showing the wave-function barrier penetration effect, are also plotted.

For a transverse B-field, again analogous to the III-V QW case, one gets

$$g_{QW,t}^* = \langle g_{\perp}^* \rangle + \frac{4m_e}{\hbar^2} \langle z \frac{\partial \gamma_{so}}{\partial z} \rangle, \qquad (16)$$

which is the average bulk g-factor plus an interface spinorbit contribution g_{int}^* given by

$$g_{int}^* = -\frac{4m_e}{\hbar^2} \,\delta\gamma_{so} \,L \,|f_0(L/2)|^2 \tag{17}$$

where $\delta \gamma_{so} = \gamma_{so}^{(w)} - \gamma_{so}^{(b)}$. Recall that γ_{so} is a step function in z changing from $\gamma_{so}^{(w)}$ to $\gamma_{so}^{(b)}$ at the interface; $|f_0(L/2)|^2 = |f_0(-L/2)|^2$ was also used. As in the III-V QW case, the IV-VI longitudinal-valley $g_{QW,t}^*$ does not depend on the B-field direction in the plane; therefore the g-factor anisotropy $\Delta g_{QW}^* = g_{QW,l}^* - g_{QW,t}^*$ in this case is simply given by:

$$\Delta g_{QW}^* = \langle g_{\parallel}^* - g_{\perp}^* \rangle - g_{int}^* \,. \tag{18}$$

Differently to the III-V QW case, such IV-VI g-factor anisotropy presents two contributions: a bulk average and an interface one determined by the mesoscopic (Rashba type) spin-orbit interaction. Figure 2 shows the well width dependence of such $g^*_{QW,t}$ in a PbSnTe/PbTeQW. To compare and access the different contributions to the QW g-factor, which include wave-function barrier penetration, confinement energy shift and interface SO interaction, it is also plotted the energy dependent bulk g-factors and their average.

B. Oblique valleys

For the oblique valleys instead the transverse g-factor does depend on the B-field direction in the QW plane. The transverse magnetic field actually breaks the oblique valley degeneracy, while the perpendicular one does not. Considering the specific oblique valley which sets the valley-system in the above used coordinate-system rotation, for the longitudinal $\vec{B} = B\hat{z}$ one gets:

$$< g_0 |H_z| g_0 > = \frac{\mu_0}{2} B(g_{zy}^* \sigma_y + g_{zz}^* \sigma_z),$$
 (19)

with

$$g_{zy}^* = sc < g_{\perp}^* - g_{\parallel}^* > -(s^2 r + c^2) D g_{int}$$
(20)

and

$$g_{zz}^* = \langle s^2 g_{\perp}^* + c^2 g_{\parallel}^* \rangle - s c (r-1) D g_{int}.$$
 (21)

Noting that $D = 2\sqrt{2}(1 - r^2)/(1 + 8r^2)$ for [111] and $= \sqrt{2}(1-r^2)/(1+2r^2)$ for [100] QWs we then have explicitly

$$g_{zy}^* = \frac{2\sqrt{2}}{9} \left[\langle g_{\perp}^* - g_{\parallel}^* \rangle - \frac{(8r+1)(1-r^2)}{8r^2+1} g_{int} \right], \quad (22)$$

$$g_{zz}^* = \frac{\langle 8g_{\perp}^* + g_{\parallel}^* \rangle}{9} - \frac{8}{9} \frac{(r-1)(1-r^2)}{8r^2+1} g_{int}, \quad (23)$$

for [111] QWs, and

$$g_{zy}^* = \frac{\sqrt{2}}{3} \left[\langle g_{\perp}^* - g_{\parallel}^* \rangle - \frac{(2r+1)(1-r^2)}{2r^2+1} g_{int} \right], \quad (24)$$

$$g_{zz}^* = \frac{\langle 2 g_{\perp}^* + g_{\parallel}^* \rangle}{3} - \frac{2}{3} \frac{(r-1)(1-r^2)}{2r^2+1} g_{int} \,, \quad (25)$$

for [100] QWs.

Due to the anisotropy $(r \neq 1)$, the oblique valleys are seen to present an interface contribution to their effective g-factor even for a longitudinal magnetic-field, which indeed in these structures (due to the anisotropy) does not drive the electrons along a purely transverse cyclotron orbit. Again when $g_{\perp} = g_{\parallel}$ and r = 1 the symmetrical III-V like result is recovered. In Figure 3, as a function of the PbSnTe/PbTe QW width, it is plotted the resulting longitudinal effective g-factor for the oblique valleys in both [111] and [100] QWs, given by

$$g_{o,l}^* = \sqrt{{g_{zy}^*}^2 + {g_{zz}^*}^2}$$

and which determines the Zeeman splitting $\Delta E (= \mu_0 B g_{o,l}^*)$.

The last and most anisotropic situation is that of the oblique valleys with a transverse B-field, where the crystal growth, the magnetic-field and the valley-main axis



FIG. 4. Longitudinal effective g-factor for the oblique valley electrons in PbSnTe/PbTe [111] and [100] QWs as a function of the well width.

are each along a different direction; and indeed in this case one gets:

$$\langle H_z \rangle = \frac{\mu_0}{2} B[\cos(\phi)g_{xx}^*\sigma_x + \sin(\phi)(g_{yy}^*\sigma_y + g_{yz}^*\sigma_z)],$$
(26)

where ϕ is the in-plane angle between \vec{B} and \hat{x} ,

$$g_{xx}^* = \langle g_{\perp}^* \rangle + g_{int}^* \tag{27}$$

(equal to the above longitudinal valley $g^*_{QW,t}$ except that here, as mentioned, the average of the bulk and the interface contribution g^*_{int} (Eq. (17)) are calculated with the oblique valley unperturbed energy and envelopefunction) and

$$g_{yy}^* = [\langle g_{\perp}^* + 8 g_{\parallel}^* \rangle + (8r+1) g_{int}^*]/9 \qquad (28)$$

$$g_{yz}^* = 2\sqrt{2} [\langle g_{\parallel}^* - g_{\perp}^* \rangle + (r-1) g_{int}^*] / 9, \qquad (29)$$

for [111] QWs, and

$$g_{yy}^* = \left[\langle g_{\perp}^* + 2 g_{\parallel}^* \rangle + (2r+1) g_{int}^* \right] / 3 \qquad (30)$$

$$g_{yz}^* = \sqrt{2} [\langle g_{\parallel}^* - g_{\perp}^* \rangle + (r-1) g_{int}^*]/3,$$
 (31)

for [100] QWs.

Figures 5 and 6 show the oblique valley transverse QW effective g-factor

$$g_{o,t}^* = \sqrt{\cos(\phi)^2 g_{xx}^{*2} + \sin(\phi)^2 (g_{yy}^{*2} + g_{yz}^{*2})}$$

as a function of ϕ for [111] and [100] PbSnTe/PbTe QWs, respectively, with different well widths.

To conclude it is interesting to note that a pure mesoscopic g-factor anisotropy in IV-VI QWs can be seen with the longitudinal valleys in [110] QWs. For these valleys



FIG. 5. Transverse effective g-factor for the oblique valley electrons in PbSnTe/PbTe [111] QWs, as a function of the in-plane B-field angle (with respect to \hat{x}) and for different well widths.



FIG. 6. The same as Fig. 5 for [100] QWs.

we put c=0 and s=1 and for longitudinal magnetic fields (i.e. along [110] $\parallel \hat{z})$ get

$$g^*_{QW,l} = \langle g^*_\perp \rangle,$$

while for transverse B fields

$$g^*_{QW,t} = \sqrt{\mathcal{C}^2(\langle g^*_{\perp} \rangle + g_{int})^2 + \mathcal{S}^2(\langle g^*_{\parallel} \rangle + r \, g_{int})^2}$$

where $C = cos(\phi)$ and $S = sin(\phi)$ with ϕ , as before, giving the direction of the magnetic field in the QW plane. So that if one rotates \vec{B} around \hat{y} ($\phi = 0$) gets

$$\Delta g_{QW}^* = g_{QW,t}^* - g_{QW,l}^* = g_{int} \,.$$

V. CONCLUSIONS

Summarizing, an envelope-function theory for the electron and hole effective g-factor tensor in IV-VI semiconductor QWs has been presented with analytical results for simple structure. The effective g-factor in these structures is seen to be renormalized by the confining mesoscopic potential through the Rashba spin-orbit coupling. Contrary to the known III-V QWs, in IV-VI QWs the effective g-factor presents anisotropy not only due to the magnetic field direction but also due the actual crystal growth and specific L-valley being considered.

VI. ACKNOWLEDGMENTS

EAAS is thankful to the Scuola Normale Superiore di Pisa, for the kind hospitality. Support from the brazilian agencies FAPESP and CNPq is also acknowledged.

- P. Yu and M. Cardona, Fundamentals of Semiconductor (Springer, 2001).
- [2] J. O. Dimmock, Physics of semimetals and narrow-gap semiconductors, Eds D. L. Carter and R.T. Bate (Perg-

amon 1971), 319.

- [3] M. M. Hasegawa and E. A. de Andrada e Silva, Physical Review B, 68, 205309 (2003).
- [4] E. Abramof, E. A. de Andrada e Silva, S. Ferreira, P. Motisuke, P. Rappl, and A. Ueta, Physical Review B, 63, 085304 (2001).
- [5] P. McCann, IV-VI Semiconductors for Mid-infrared Optoelectronic Devices, Springer Series in Optical Sciences Vol. 118, Ed. Anthony Krier, 237 (2006).
- [6] G. Springholz and G. Bauer, Phys. Status Solidi B, 244, 27522767 (2007).
- [7] L. Elizondo, P. J. McCann, S. Elizondo, and S. Shi, *IVVI Semiconductor Nanostructures: Physics and Applications* (VDM Verlag, 2009).
- [8] R. Buczko and L. Cywiński, Phys. Rev. B, 85, 205319 (2012).

- [9] M. Z. Hasan and C. L. Kane, Rev. Mod. Phys., 82, 3045 (2010).
- [10] E. A. de Andrada e Silva, Physical Review B, 60, 8859 (1999).
- [11] E. Ridolfi, Tesi di laurea, Universitá di Pisa (2013).
- [12] F. Stern and W. E. Howard, Phys. Rev., 163, 816 (1967).
- [13] M. T. Sandoval, A. Ferreira da Silva, E. de Andrada e Silva, and G. La Rocca, Physical Review B, 86, 195302 (2012).
- [14] F. A. Baron, A. A. Kiselev, H. D. Robinson, K. W. Kim, K. L. Wang, and E. Yablonovitch, Phys. Rev. B, 68, 195306 (2003).
- [15] H. Schaber and R. Doezema, Solid State Communications, **31**, 197 (1979).
- [16] T. Ichiguchi, S. Nishikawa, and K. Murase, Solid State Communications, 34, 309 (1980).